

PERSONAL PROTECTIVE EQUIPMENT



High Temperature Technical Textile

Article No.: 7125FT218

High-silica fabrics are a new-generation heat resistant material. Glass fibre products with a high SiO2 content are excellent high temperature insulators and can be used over long periods without losing the properties and without melting and vaporising.



Fiber Type: Silica

Composition: $96\% SiO_2$, $A1_2O_3 3.5 +/-0.5\%$

Finish/Coating: Vermiculite Coating

Service Temp.: 1050°C Melting Temp.: 1600°C Color: Gold

	Metric	Test Methods
	12H Satin	
Warp	19 +/-1 yarn/cm	DIN 53853
Weft	11 +/-1 yarn/cm	DIN 53853
	1140 +70/-50 g/m2	DIN 12127
	1.25 +/-1 0.15 mm	DIN EN ISO 5084
	152 +2/-1 cm	DIN EN 1773
	45 m	
Warp	2000 N/2.5cm	EN ISO 13934.1
Weft	1500 N/2.5cm	EN ISO 13934.1
	Weft	12H Satin Warp 19 +/-1 yarn/cm Weft 11 +/-1 yarn/cm 1140 +70/-50 g/m2 1.25 +/-1 0.15 mm 152 +2/-1 cm 45 m Warp 2000 N/2.5cm

Roll Size	Blanket Sizes
1 x 45 (mtrs)	2 x 2 (mtrs)
	2 x 4 (mtrs)

Application

- As insulation & protection applications, such as sealing, packaging, protective screens
- As drop cloth for welding & fire curtains
- As reinforcement for acid resistant composites for filtration of molten metal & furnace exhaust, etc.

PPE CUSTOMIZATION PROGRAM



Customize size and stitching as per client's requirements

- Custom size blankets are stitched with fibre glass texturized thread, which bears high tensile strength, heat resistance and resistance against water, acids and organic solvents.
- Length of the blanket to be sewn together with an overlap of atleast 20-25mm (1").
- Atleast 25mm (1") overlap all around the blanket.
- Properly secured with heavy duty brass eyelets around the blanket with 500mm (24") gap.
- Velcro pastening can also be provided.

Distance of eyelets or velcro my vary as per client's requirements.

Accessories





This Article Data Sheet (ADS) is designed and produced by FLOWTRONIX (FT) covered under the intellectual property law. Any reproduction in whole or in part is strictly prohibited without written approval. FT HT 1206-3.2

